





## Specifications

DESCRIPTION	DATA	NORM
Type de revêtement / Type of flooring	Dalle Plombante Amovible (DPA) touffetée / Tufted loose lay Tile	
Composition fibreuse / Pile Fibre	100% Polyamide (Teint masse/Solution dyed)	
Jauge / Gauge	5/64 loop pile	
Densité / Tuft Density	213 200 Stitches	ISO 1763
Poids de fil / Total pile mass	725 g/m <sup>2</sup>	ISO 8543
Masse de velours utile / Mass of pile above the substrate	370 g/m <sup>2</sup>	ISO 8543
Epaisseur velours utile / Thickness of pile above the substrate	2,9 mm	ISO 1766
Densité du velours de surface / Surface pile density	0,128 g/cm <sup>3</sup>	ISO 8543
Masse totale / Total Weight	3869g/m <sup>2</sup>	ISO 8543
Epaisseur totale / Total Thickness	9,8 mm	ISO 1765
Premier dossier / Primary Backing	Non tissé / Non woven primary backing	
Envers / Backing	Fibres synthétiques 100% recyclées / 100% recycled fibers	
Dimensions / Tile Size	50x50cm	
Dalles par boîte / Tiles per Box	16 =4m <sup>2</sup>	
Sens de pose / Installation		

## Technical performances









Classe de confort / Luxury Class - LC1



Classe d'usage / Overall use class (Classification EN 1307) - 23/33 / Commercial Heavy

Classement feu / Fire rating (EN 13501-1): Bfl-s1



				RHO - LRV	
				9 colors	%
 Heated Floor ISO 10456 0,13 m <sup>2</sup> KW	 Castor Chair EN 985 Passed R <sub>≥3,4</sub>	130	21,5%		
		131	17,5%		
 Electrostatic prop. ISO 6356 ≤ 2,0kV ISO 10965 RT ≈ 10 <sup>10</sup> Ω	 Colour Fastness EN 105 - B02 7/8	139	13,2%		
		230	18,7%		
 Dimensional Stability EN 986 ≤ 0,20%	 Impact noise reduction EN ISO 10143-3 ΔL <sub>(w)</sub> 26 dB	239	8,0%		
		303	9,5%		
 N° 0679-CPR-1316 EN 14041 : 2004 +AC: 2006	 Sound absorption ISO 11654 α <sub>w</sub> = 0,25 (H) 125Hz 250Hz 500Hz 1000Hz 2000Hz 4000Hz 0,01α□ 0,06α□ 0,48α□ 0,19α□ 0,25α□ 0,33α□	471	13,8%		
		592	7,5%		
		593	6,2%		

## Environmental issues



Les informations ci-dessus peuvent subir des modifications au profit d'une future amélioration / The above information is subject to modifications for the benefit of further improvement.