

## Specifications

DESCRIPTION	NORM	DATA
Composition fibreuse / Pile Fibre		100% Polyamide (Teint masse/Solution dyed)
Jauge / Gauge		1/10 loop pile
Densité / Tuft Density	ISO 1763	196 800 Stitches/m <sup>2</sup>
Poids de fil / Total pile mass	ISO 8543	500 g/m <sup>2</sup>
Masse de velours utile / Mass of pile above the substrate	ISO 8543	290 g/m <sup>2</sup>
Epaisseur velours utile / Thickness of pile above the substrate	ISO 1766	2,6 mm
Densité du velours de surface / Surface pile density	ISO 8543	0,111 g/cm <sup>3</sup>
Masse totale / Total Weight	ISO 8543	4270 g/m <sup>2</sup>
Epaisseur totale / Total Thickness	ISO 1765	6.3 mm
Premier dossier / Primary Backing		Non tissé / Non woven primary backing
Envers / Backing		Matières recyclées renforcées par un voile de verre Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Dimensions / Tile Size		50x50cm
Dalles par boîte / Tiles per Box		20 = 5m <sup>2</sup>
Sens de pose / Installation		

## Technical performances



Classification EN 1307 - 33 / Commercial Heavy

Luxury Class - LC1



Classement UPEC NF 262 - U<sub>3</sub>P<sub>3</sub>E<sub>1</sub>C<sub>0</sub> (certificat n° 349T-001.1)

Feu / Fire rating EN 13501-1 : BflS1



Heated Floor		Impact noise reduction		RHO - LRV	
	ISO 10456 0,08 m <sup>2</sup> K/W		EN ISO 10143-3 ΔL <sub>(w)</sub> 24 dB	7 colors	%
Electrostatic prop.		Sound absorption		023	10,3%
	ISO 6356 ≤ 2,0kV		ISO 11654 α <sub>w</sub> = 0,15 (H)	028	3,9%
Dimensional Stability		Colour Fastness		032	18,2%
	EN 986 ≤ 0,10%		EN 105 - B02 7/8	036	11,9%
CE		Castor Chair		038	7,2%
N° 0679-CPR-0196			EN 985 Passed R <sub>≥2,4</sub>	062	21,9%
07				068	15,9%
EN 14041 : 2004					

## Environmental issues



Les informations ci-dessus peuvent subir des modifications au profit d'une future amélioration / The above information is subject to modifications for the benefit of further improvement.