

## Specifications

DESCRIPTION	NORM	DATA
Composition fibreuse / Pile Fibre		100% Polyamide (Teint masse/Solution dyed)
Jauge / Gauge		1/10 loop pile
Densité / Tuft Density	ISO 1763	196 800 Stitches/m <sup>2</sup>
Poids de fil / Total pile mass	ISO 8543	510 g/m <sup>2</sup>
Masse de velours utile / Mass of pile above the substrate	ISO 8543	300 g/m <sup>2</sup>
Épaisseur velours utile / Thickness of pile above the substrate	ISO 1766	2.2 mm
Densité du velours de surface / Surface pile density	ISO 8543	0,136 g/cm <sup>3</sup>
Masse totale / Total Weight	ISO 8543	4290 g/m <sup>2</sup>
Épaisseur totale / Total Thickness	ISO 1765	6.0 mm
Premier dossier / Primary Backing		Non tissé / Non woven primary backing
Envers / Backing		Matières recyclées renforcées par un voile de verre Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Dimensions / Tile Size		50x50cm
Dalles par boîte / Tiles per Box		20 = 5m <sup>2</sup>
Sens de pose / Installation		

## Technical performances



Classification EN 1307 - 33 / Commercial Heavy  
Luxury Class - LC1



Feu / Fire rating EN 13501-1 : Bfl-s1

				RHO - LRV	
				9 colors	%
<b>Heated Floor</b>  ISO 10456    0,08 m <sup>2</sup> K/W	<b>Impact noise reduction</b>  EN ISO 10143-3    ΔL <sub>(w)</sub> 22 dB	017	4,5%		
		025	6,4%		
<b>Electrostatic prop.</b>  ISO 6356    ≤ 2,0kV ISO 10965    RT ≈ 10 <sup>10</sup> Ω	<b>Sound absorption</b>  ISO 11654    α <sub>w</sub> = 0,10 (H)	028	3,7%		
		032	26,6%		
<b>Dimensional Stability</b>  EN 986    ≤ 0,10%	<b>Colour Fastness</b>  EN 105 - B02    7/8	034	14,8%		
		038	10,4%		
 N° 0679-CPR-0196 12 EN 14041 : 2004	<b>Castor Chair</b>  EN 985    Passed R <sub>≥2,4</sub>	045	11,5%		
		147	3,7%		
		172	25,8%		

## Environmental issues

**LEED**

Répond à la démarche  
**HQE**

